

## Description

The tde patch and trunk cables are manufactured completely at the German facility in Ohrte. Production processes at tde meet the latest standards, and the company has one of the most up-to-date fiber optic assembly houses in Europe. Fiber optic patch cables and trunk cables are manufactured in many different configurations using highly automated processes on two independent mass production lines. The range of products on offer encompasses the entire spectrum of connector types available on the market. Production capacity is around 100,000 fiber optic connectors per month, and this can be ramped up easily whenever required. To guarantee consistently top quality, only the best components from renowned vendors are used. All tde production staff have the necessary qualifications and education, and have been well trained in using specialist technical equipment such as laser cleavers and glue-dispensing robots.

Each cable application is subjected to a full test procedure comprising interferometer measurements, insertion loss and return loss measurements and a final visual inspection to ensure that only 100% error-free products are shipped to the customer.

Products made by tde perform at least internationally accepted quality standards and norms. The quality management system is ISO 9001, ISO 14001 and TL9000 certified.



## Technical Data

### FO Connectors

|                       |                         |
|-----------------------|-------------------------|
| Connector Type        | ST                      |
| Housing               | Metal                   |
| Ferrule               | Zirconia Straight Split |
| Ferrule Hole          | 125.5 $\mu$             |
| Ferrule Concentricity | $\leq 0.6 \mu$          |
| Mating Cycles         | 500                     |
| Operating Temperature | -40°C up to +75°C       |
| Strain Relief to      | 150 N                   |
| Manufacturer          | tde                     |

### Optical performance

| Fiber       | Type | Wavelength | Insertion loss typ. | Insertion loss max. | Return loss min. |
|-------------|------|------------|---------------------|---------------------|------------------|
| 9/125 $\mu$ | ST   | 1550 nm    | $\leq 0.20$ dB      | 0.45 dB             | 45 dB            |

## tde - FO Fiberpigtail ST 9/125 $\mu$ OS2 Length: 2m

### FO Cables

|              |  |
|--------------|--|
| Tight Buffer | Low smoke (IEC 61034 and EN 50268) and free of halogens (LSOH)   |
|              | Non corrosive after IEC 60754-2 and EN 50267                     |
|              | Flame resistant after IEC 60332-3C and EN 50266-2-4              |
|              | Completely dry design  |
|              | Free from metal, no grounding problems and potential differences |
|              | Tight Buffer for simple and direct connector mounting            |

### Characteristics

|  |                  |
|--|------------------|
| Fiber Count                              | 1 (Tight Buffer) |
| Core- $\emptyset$                        | 0.9 mm           |
| Coreweight                               | 1 kg/km          |
| Min. Bending radius - Installation       | 30 mm            |
| Min. Bending radius - Operation          | 30 mm            |
| Removal                                  | 1500 mm          |
| Fire load                                | 0.15 MJ/m        |
| Temperature range - Installation         | -5 to +50°C      |
| Temperature range - Operation            | -20 to +60°C     |
| Temperature range - Transport / Lagerung | -25 to +70°C     |

### FO Fiber

|                            |  |
|----------------------------|--|
| Type                       | Corning Ultra SMF-28 <sup>®</sup> 09/125 $\mu$ OS2 singlemode fiber  |
| Maximum Attenuation        | At 1310 nm max. 0.32 dB/km<br>At 1383 nm max. 0.32 dB/km<br>At 1490 nm max. 0.21 dB/km<br>At 1550 nm max. 0.18 dB/km<br>At 1625 nm max. 0.20 dB/km   |
| Attenuation vs. Wavelength | Range: 1285 - 1330 nm; Ref. $\lambda$ : 1310 nm; Max. Difference: 0.03 dB/km<br>Range: 1525 - 1575 nm; Ref. $\lambda$ : 1550 nm; Max. Difference: 0.02 dB/km   |
| Macrobend Loss             | Mandrel Radius: 10mm; Number of Turns: 1; Wavelength: 1550nm; Induced Attenuation: $\leq$ 0.50 dB<br>Mandrel Radius: 10mm; Number of Turns: 1; Wavelength: 1625nm; Induced Attenuation: $\leq$ 1.5 dB<br>Mandrel Radius: 15mm; Number of Turns: 10; Wavelength: 1550nm; Induced Attenuation: $\leq$ 0.05 dB<br>Mandrel Radius: 15mm; Number of Turns: 10; Wavelength: 1625nm; Induced Attenuation: $\leq$ 0.30 dB<br>Mandrel Radius: 25mm; Number of Turns: 100; Wavelength: 1310nm, 1550nm, 1625nm; Induced Attenuation: $\leq$ 0.01 dB |
| Point Discontinuity        | Wavelength: 1310 nm; Point Discontinuity: $\leq$ 0.05 dB<br>Wavelength: 1550 nm; Point Discontinuity: $\leq$ 0.05 dB   |

## tde - FO Fiberpigtail ST 9/125 $\mu$ OS2 Length: 2m

|   |   |
|---|---|
| Cable Cutoff Wavelength ( $\lambda_{ccf}$ ) | $\lambda_{ccf} \leq 1260$ nm  |
| Mode-Field Diameter                         | At 1310 nm = $9.2 \pm 0.4$ $\mu$ m<br>At 1550 nm = $10.4 \pm 0.5$ $\mu$ m   |
| Dispersion                                  | At 1550 nm = $\leq 18.0$ [ps/(nm*km)]<br>At 1625 nm = $\leq 22.0$ [ps/(nm*km)]  |
|   | Zero Dispersion Wavelength ( $\lambda_0$ ): $1304$ nm $\leq \lambda_0 \leq 1324$ nm<br>Zero Dispersion Slope ( $S_0$ ): $\leq 0.092$ ps/(nm <sup>2</sup> *km) |
| Polarization Mode Dispersion (PMD)          | PMD Link Design Value = $\leq 0.04$ ps/ $\sqrt$ km<br>Maximum Individual Fiber = $\leq 0.1$ ps/ $\sqrt$ km  |

### Dimensional Specifications

|                                |                                  |
|--------------------------------|----------------------------------|
| Fiber Curl                     | $\geq 4.0$ m radius of curvature |
| Cladding Diameter              | $125.0 \pm 0.7$ $\mu$ m          |
| Core-Clad Concentricity        | $\leq 0.5$ $\mu$ m               |
| Cladding Non-Circularity       | $\leq 0.7\%$                     |
| Coating Diameter               | $242 \pm 5$ $\mu$ m              |
| Coating-Cladding Concentricity | $< 12$ $\mu$ m                   |

### Environmental Specifications

| Environmental Test           | Test Condition              | Induced Attenuation 1310 nm, 1550 nm & 1625 nm |
|------------------------------|-----------------------------|--|
| Temperature Dependence       | -60°C to +85°C              | $\leq 0.05$                                    |
| Temperature Humidity Cycling | -10°C to +85°C up to 98% RH | $\leq 0.05$                                    |
| Water Immersion              | 23°C $\pm$ 2°C              | $\leq 0.05$                                    |
| Heat Aging                   | 85°C $\pm$ 2°C              | $\leq 0.05$                                    |
| Operating Temperature Range  | -60°C to +85°C              |  |

### Mechanical Specifications

|            |  |
|------------|--|
| Proof Test | The entire fiber length is subjected to a tensile stress $\geq 100$ kpsi (0.69 GPa). |
| Length     | Fiber lengths available up to 63.0 km/spool.   |

### Performance Characterizations

|                    |             |
|--------------------|-------------|
| Core Diameter      | 8.2 $\mu$ m |
| Numerical Aperture | 0.14        |

## tde - FO Fiberpigtail ST 9/125 $\mu$ OS2 Length: 2m

|   |  |
|---|--|
| Effective Group Index of Refraction                     | 1310 nm: 1.4676<br>1550 nm: 1.4682                               |
| Fatigue Resistance Parameter (nd)                       | 20   |
| Coating Strip Force                                     | Dry: 0.6 lbs (3N)<br>Wet: 14 days room temperature: 0.6 lbs (3N) |
| Rayleigh Backscatter Coefficient (for 1 ns Pulse Width) | 1310 nm: -77 dB<br>1550 nm: -82 dB                               |

| Art.-No.         | Description  |
|------------------|--|
| L-ST/-09F00200   | tde - FO Fiberpigtail ST 9/125 $\mu$ OS2 Length: 2m    |
| L-ST/-50F00200   | tde - FO Fiberpigtail ST 50/125 $\mu$ OM2 Length: 2m   |
| L-ST/-50F3-00200 | tde - FO Fiberpigtail ST 50/125 $\mu$ OM3 Length: 2m   |
| L-ST/-62F00200   | tde - FO Fiberpigtail ST 62,5/125 $\mu$ OM1 Length: 2m |