


ISO 9001 TL 9000 ISO 14001

FO Breakoutl cable 8x E2000 APC/8x E2000 APC 8E9/125µ OS2 LSHF, Length: xxxx



# tde - Fiber Optic Assemblies

The tde patch and trunk cables are manufactured completely at the German facility in Ohrte. Production processes at tde meet the latest standards, and the company has one of the most up-to-date fiber optic assembly houses in Europe. Fiber optic patch cables and trunk cables are manufactured in many different configurations using highly automated processes on two independent mass production lines. The range of products on offer encompasses the entire spectrum of connector types available on the market. Production capacity is around 100,000 fiber optic connectors per month, and this can be ramped up easily whenever required. To guarantee consistently top quality, only the best components from renowned vendors are used. All tde production staff have the necessary qualifications and education, and have been well trained in using specialist technical equipment such as laser cleavers and glue-dispensing robots.

Each cable application is subjected to a full test procedure comprising interferometer measurements, insertion loss and return loss measurements and a final visual inspection to ensure that only 100% error-free products are shipped to the customer.

Products made by tde perform at least internationally accepted quality standards and norms. The quality management system is ISO 9001, ISO 14001 and TL9000 certified.



#### tde® trans data elektronik GmbH

#### **Headquarter address:**

Lingener Str. 2 D-49626 Bippen/Ohrte Tel.: +49 5435 9511 0 Fax.: +49 5435 9511 32

#### Sales office address:

Prinz-Friedrich-Karl-Str. 46 D-44135 Dortmund Tel.: +49 231 8805 61 13 Fax.: +49 231 8805 61 15

info@tde.de | www.tde.de



# FO Breakoutl cable 8x E2000 APC/8x E2000 APC 8E9/125µ OS2 LSHF, Length: xxxx

# **Technical Data**

# **FO Connectors**

| Туре                  | E2000 APC        |
|-----------------------|------------------|
| Ferrule               | Ceramic          |
| Ferrule Hole          | 125.5 μ          |
| Ferrule Concentricity | $\leq 0.6 \ \mu$ |
| Connector Colour      | Green            |
| Lever Colour          | Green            |
| Boot Colour           | Green            |
| Manufacturer          | RDM              |

## **Optical performance**

| Fiber  | Туре      | Wavelength | Insertion loss typ. | Insertion loss max. | Return loss min. |
|--------|-----------|------------|---------------------|---------------------|------------------|
| 9/125µ | E2000 APC | 1550 nm    | $\leq$ 0.20 dB      | 0.45 dB             | 70 dB            |

# **FO Cables**

## Cable Data

| Туре           | IVHH08E9/125 |
|----------------|--------------|
| Fiber Amount   | 8            |
| Construction   | 8            |
| Outer Diameter | 9.3 mm       |
| Tolerance      | ± 0.3 mm     |

| Subcable Diameter | 2.0 (± 0.1 mm)   |
|-------------------|--|
| Strength Members  | Aramid yarns   |
| Outer Jacket      | LSOH (Halogen free, low smoke, flame retardant thermoplastic compound) |
| Jacket Colour     | Yellow   |
| Standard printing | "t d e – IVHH08E09-2.0" and sequential meter marking + Lot number      |

## Mechanical/Thermal Characteristics

| Fiber Amount          | 8                             |
|-----------------------|-------------------------------|
| Weight                | 70 kg/km                      |
| Tensile load          | 1200 N                        |
| Bending radius        | 20 x outer diameter           |
| Operating temperature | -5°C bis +60°C IEC 60794-2-20 |
| Fire resistance       | EN 50266, IEC 60332           |
| Halogen content       | EN 50267, IEC 60754           |
| Smoke density         | EN 50268, IEC 61034-1/-2      |





# FO Breakoutl cable 8x E2000 APC/8x E2000 APC 8E9/125µ OS2 LSHF, Length: xxxx

## **Special features**

| Characteristics | Fiber and aramid yarn free movable in the compound |
|-----------------|--|
| Identification  | Numbers, min. every 25cm on subcables              |

# FO Fiber

| Туре                               | Corning SMF-28e+® 09/125µ OS2 G.652.D singlemode fiber   |
|------------------------------------|--|
| Maximum Attenuation                | At 1310 nm max. 0.33 - 0.35 dB/km<br>At 1383 ± 3 nm max. 0.31 - 0.35 dB/km<br>At 1490 nm max. 0.21 - 0.24 dB/km<br>At 1550 nm max. 0.19 - 0.20 dB/km<br>At 1625 nm max. 0.20 - 0.23 dB/km  |
| Attenuation vs. Wavelength         | Range: 1285 - 1330 mm; Ref. $\lambda$ : 1310 nm; Max. Difference: 0.03 dB/km<br>Range: 1525 - 1575 mm; Ref. $\lambda$ : 1550 nm; Max. Difference: 0.02 dB/km   |
| Macrobend Loss                     | Mandrel Diameter:32mm; Number of Turns: 1; Wavelength: 1550nm; Induced Attenuation: ≤0.03 dB<br>Mandrel Diameter:50mm; Number of Turns: 100; Wavelength: 1310nm; Induced Attenuation: ≤0.03 dB<br>Mandrel Diameter:50mm; Number of Turns: 100; Wavelength: 1550nm; Induced Attenuation: ≤0.03 dB<br>Mandrel Diameter:60mm; Number of Turns: 100; Wavelength: 1625nm; Induced Attenuation: ≤0.03 dB |
| Point Discontinuity                | Wavelength: 1310 nm; Point Discontinuity: $\leq$ 0.05 dB Wavelength: 1550 nm; Point Discontinuity: $\leq$ 0.05 dB  |
| Cable Cutoff Wavelength (λccf)     | $\lambda ccf \le 1260 \text{ nm}$  |
| Mode-Field Diameter                | At 1310 nm = 9.2 ± 0.4 μm<br>At 1550 nm = 10.4 ± 0.5 μm  |
| Dispersion                         | At 1550 nm = $\leq$ 18.0 [ps/(nm*km)]<br>At 1625 nm = $\leq$ 22.0 [ps/(nm*km)]   |
|                                    | Zero Dispersion Wavelength ( $\lambda_0$ ): 1310 nm $\leq \lambda_0 \leq$ 1324 nm Zero Dispersion Slope ( $S_0$ ): $\leq$ 0.092 ps/(nm <sup>2</sup> *km)   |
| Polarization Mode Dispersion (PMD) | PMD Link Design Value = $\leq 0.06 \text{ ps/}\sqrt{\text{km}}$<br>Maximum Individual Fiber = $\leq 0.1 \text{ ps/}\sqrt{\text{km}}$   |
| Norm                               | ITU-T Recommendation G.652 (Tables A, B, C, and D)<br>IEC Specifications 60793-2-50 Type B1.3<br>TIA/EIA 492-CAAB<br>Telcordia Generic Requirements GR-20-CORE<br>ISO 11801 OS2  |

#### **Dimensional Specifications**

| Fiber Curl                     | $\geq$ 4.0 m radius of curvature |
|--------------------------------|----------------------------------|
| Cladding Diameter              | 125.0 ± 0.7 μm                   |
| Core-Clad Concentricity        | ≤ 0.5 μm                         |
| Cladding Non-Circularity       | ≤ 0.7%                           |
| Coating Diameter               | 242 ± 5 μm                       |
| Coating-Cladding Concentricity | < 12 µm                          |

## **Environmental Specifications**

| Environmental Test           | Test Condition              | Induced Attenuation 1310 nm, 1550 nm & 1625 nm |
|------------------------------|-----------------------------|--|
| Temperature Dependence       | -60°C to +85°C              | ≤ 0.05   |
| Temperature Humidity Cycling | -10°C to +85°C up to 98% RH | ≤ 0.05   |



# FO Breakoutl cable 8x E2000 APC/8x E2000 APC 8E9/125µ OS2 LSHF, Length: xxxx

| Water Immersion             | 23°C ± 2°C     | ≤ 0.05 |
|-----------------------------|----------------|--------|
| Heat Aging                  | 85°C ± 2°C     | ≤ 0.05 |
| Operating Temperature Range | -60°C to +85°C |        |

#### **Mechanical Specifications**

| Proof Test | The entire fiber length is subjected to a tensile stress $\geq$ 100 kpsi (0.7 GPa). |
|------------|---|
| Length     | Fiber lengths available up to 63.0 km/spool.  |

#### **Performance Characterizations**

| Core Diameter  | 8.2 µm   |
|--|--|
| Numerical Aperture   | 0.14   |
| Zero Dispersion Wavelength ( $\lambda_0$ )                 | 1317 nm  |
| Zero Dispersion Slope (S <sub>0</sub> )                    | 0.088 ps/(nm <sup>2*</sup> km)                                   |
| Effective Group Index of Refraction                        | 1310 nm: 1.4676<br>1550 nm: 1.4682                               |
| Fatigue Resistance Parameter (nd)                          | 20   |
| Coating Strip Force  | Dry: 0.6 lbs (3N)<br>Wet: 14 days room temperature: 0.6 lbs (3N) |
| Rayleigh Backscatter Coefficient<br>(for 1 ns Pulse Width) | 1310 nm: -77 dB<br>1550 nm: -82 dB                               |

# **Product variants & accessories**

| ArtNo.              | Description   |
|---------------------|---|
| L-E2A/E2A09V04Exxxx | FO Breakoutl cable 4x E2000 APC/4x E2000 APC 4E9/125µ OS2 LSHF, Length: xxxx    |
| L-E2A/E2A09V08Exxxx | FO Breakoutl cable 8x E2000 APC/8x E2000 APC 8E9/125µ OS2 LSHF, Length: xxxx    |
| L-E2A/E2A09V12Exxxx | FO Breakoutl cable 12x E2000 APC/12x E2000 APC 12E9/125µ OS2 LSHF, Length: xxxx |
| L-E2A/E2A09V24Exxxx | FO Breakoutl cable 24x E2000 APC/24x E2000 APC 24E9/125µ OS2 LSHF, Length: xxxx |